

▶ PRIMA PLAIN



▲ Prima Plain



Prima Plain Tegular

PRIMA PLAIN



| PRIMA PLAIN | BOARD | TEGULAR | MICROLOOK |
|-------------|--|------------------------------|------------------------------------|
| | Prelude XL/TL 24 mm | Prelude XL/TL 24 mm | Prelude XL/TL 15 mm Silhouette |
| | | | |
| | 600 x 600 x 15 mm 9587 M 625 x 625 x 15 mm 9587 D 600 x 1200 x 15 mm 9588 M 625 x 1250 x 15 mm 9588 D | 9589 M 9589 D | 9590 M 9590 D |

| EEA | A2-s1, d0 |
|-------|---|
| A | Klasse B1 (Ö-Norm B 3800) |
| B + L | Klasse A1 (NBN S 21-203) |
| CH | 6q3 (TA VKF) |
| CZ | B (CSN 730823) |
| D | Klasse B1 (DIN 4102) |
| DK | Klasse A (NBK 14) |
| E | M1 (UNE 23727: 1990) |
| F | MO (NFP 92-510) |
| FIN | Class 2 (NBK 14) |
| I | Classe 0 (D.M. 03/09/01) |
| N | In 1 (NBK 14) |
| NL | Klasse 2 (NEN 6065-6066) |
| PL | Niezpalny (PN-B-02874: 1996) |
| RUS | Hard combustible (G-1): GOST 30244-94; V1, D1, T1 NPB 244-97 |
| S | Ytskikt Klass 1 (NBK 14) |
| SK | B (STN 730823) |
| UK | Class 0/Class 1 (BS 476) |

| | Hz | | | | | | |
|---------------------|----------------|------|------|------|------|------|------|
| | NRC | 125 | 250 | 500 | 1000 | 2000 | 4000 |
| EN 20354 & EN 11654 | 0.15(L) | 0.15 | 0.30 | 0.25 | 0.15 | 0.10 | 0.15 |

| | |
|-----------------------|---------------------|
| | Dncw = 37 dB |
| EN 20140-9 & EN 717-1 | |

| | | | | | | | |
|--|---|--|------|--|---------|--|------------------------------|
| | $\lambda = 0.052 - 0.057 \text{ W/m}^{\circ}\text{K}$ | | 90 % | | 95 % RH | | $\approx 4.0 \text{ kg/m}^2$ |
|--|---|--|------|--|---------|--|------------------------------|

- Please contact our Internal Technical Sales Group for further details.
- Pour de plus amples informations merci de contacter notre Service Information Plafonds.
- Weitere Informationen erhalten Sie von unserem Kundenservice. Änderungen vorbehalten.
- Voor meer informatie kunt u contact opnemen met Market Service Center.
- Per ulteriori dettagli consultare il nostro Ufficio Commerciale.
- Para más detalles, por favor, contacte con el Servicio de Información de Techos.
- W razie dodatkowych pytań prosimy kontaktować się z biurem Armstrong w Warszawie

www.armstrong-europe.com